

SULFACAL FINE POUILLON

Food, Agriculture and Environment

PRODUCT DESCRIPTION

Sulfacal Fine Pouillon is a natural fine gypsum grade obtained from naturally occurring mineral directly from a quarry. This product is used to improve the structure of clay soils in agriculture and sports grounds. It is also used as a natural fertiliser or as a source of sulphur in fertilizers' compositions.

PRODUCT BENEFITS

- + Naturally occurring Gypsum
- + Fine particle size
- + Added calcium and sulfur for soil amendment

APPLICATIONS

Agriculture

TECHNICAL INFORMATION

Chemical Properties	
Chemical Name	Calcium Sulphate Dihydrate
Minimum gypsum purity %	79.5%
Water of crystallization %	>16.65%
Moisture Content %	<2.5%
Chemical Composition	CaSO ₄ ·2H ₂ O
Physical Properties	
Seive Analysis (Mesh size & % weight retained)	<15% retained at 5 mm >25% retained at 1600 µm >80% retained at 125 µm
Bulk density (loose) kg / m ³	1080

The technical data outlined represents typical figures only. For further details, please contact Saint-Gobain Formula directly.

PACKAGING AND SHELF LIFE

	Packaging Available	Shelf Life (Month)
Big Bag	600 kg	The technical properties indicated in this document correspond to properties upon receipt of goods.
Bulk	29 - 30 T	The technical properties indicated in this document correspond to properties upon receipt of goods.

When stored under dry conditions and in its original packaging, the product will have a specified shelf life that commences from the date of manufacture that is displayed on each sack. Shelf life depends on the packaging type. For those products where a defined 'best before' date is applicable, BBE (Best Before End) followed by the date will be displayed on each sack.

STORAGE

Plaster based products are not recommended for conditions where they are likely to be located externally or in any way subjected to weathering or excessive dampness.

Absorption of moisture can result in changes to physical properties, including a reduction in the set strength of plasters and also a lengthening of setting time.

Gypsum minerals can be affected by absorption of moisture and may change physical properties.

To help protect the product during use, open or part used bags should be carefully folded and closed. Each bag is date stamped and stocks should be rotated so that the oldest material is used first.

ENVIRONMENT, HEALTH AND SAFETY

Material Safety Data Sheets of Saint-Gobain Formula plasters and gypsum minerals are available for all products and may be obtained directly on our website in the product and documentation sections. No liability is accepted by Saint-Gobain Formula for injury to any person or loss or damage to property by improper use of the product.

NOTIFICATION

The plaster to water ratios quoted are those used in Saint-Gobain Formula's standard test methods and are not necessarily those used in practice. The precise consistency to use will need to be adjusted to suit the individual application. Changes to plaster to water ratio will influence product performance, particularly setting time and strength. Unless otherwise stated, Saint-Gobain Formula's standard test methods apply. To obtain a copy of the test method, please contact Saint-Gobain Formula directly. This literature cancels and replaces any previous document. All information given is provided in good faith and may be subject to change. It's advisable to contact Saint-Gobain Formula in case of any doubt arising from the content of such information.

CONTACT

*For any information, please visit our website
www.saintgobainformula.com*



Sales contact



Documentation



Technical information



Global information