

# SUPRADURO SM09

Ceramics

## PRODUCT DESCRIPTION

Supraduro SM09 is a formulated hemihydrate plaster produced from naturally occurring gypsum mineral. It is used in the ceramic industry to produce working moulds for spagless casting of sanitaryware. It can also be used in slip casting for sanitaryware and tableware.

## PRODUCT BENEFITS

- + Design for spagless & slip casting
- + Good dewatering
- + Consistent absorption
- + Smooth mould surface

## APPLICATIONS

Sanitaryware, Tableware

## TECHNICAL INFORMATION

Plaster to Water Ratio	
Plaster to Water Ratio (by weight)	1.33 : 1
Water to Plaster Ratio (by weight)	75%
Plaster to Water mix Ratio (by weight)	133/100
Chemical Properties	
Chemical Name	Calcium Sulphate Hemihydrate
Chemical Composition	CaSO <sub>4</sub> .1/2 H <sub>2</sub> O
Min. Gypsum Purity (%)	92%
Colour	off-white
Setting Parameters	
Vicat Ring Fluidity (cm)	19-24
Initial setting time (minutes)	13-18
Final setting time (minutes)	20-30
Linear Expansion (%)	max. 0.20
Mechanical Properties	
Flexural Strength (MPa)	min. 4.5
Physical Properties	
Particle Size Distribution (mesh size and % weight retained)	Sieve - weight retained +90µm : max. 2,50%
Loose bulk density (kg/m <sup>3</sup> )	620-720

The technical data outlined represents typical figures only. For further details, please contact Saint-Gobain Formula directly.

## INSTRUCTIONS FOR USE

The recommended plaster to water ratio is between 1,33 and 1,43: 1. Add the weighed quantity of plaster slowly into the measured volume of water and allow to soak. The mixing time is approx. 3 to 6 minutes, depending on batch size. For consistent results, attention must be given to the correct proportioning and mixing of the plaster and water. Recommend to mix with chilled water (8 - 15°C). Mixing utensils should always be clean and free from set plaster. Do not mix fresh plaster with other that was mixed previously. Changes to plaster to water ratio will influence product performance, particularly setting time, strength and absorption capability.

## PACKAGING AND SHELF LIFE

	Packaging Available	Shelf Life (Month)
Bag	25 kg	6 months
BigBag	1 T & 1.1 T	6 months

When stored under dry conditions and in its original packaging, the product will have a specified shelf life that commences from the date of manufacture that is displayed on each sack. Shelf life depends on the packaging type. For those products where a defined 'best before' date is applicable, BBE (Best Before End) followed by the date will be displayed on each sack.

## STORAGE

Plaster based products are not recommended for conditions where they are likely to be located externally or in any way subjected to weathering or excessive dampness.

Absorption of moisture can result in changes to physical properties, including a reduction in the set strength of plasters and also a lengthening of setting time.

Gypsum minerals can be affected by absorption of moisture and may change physical properties.

To help protect the product during use, open or part used bags should be carefully folded and closed. Each bag is date stamped and stocks should be rotated so that the oldest material is used first.

## ENVIRONMENT, HEALTH AND SAFETY

Material Safety Data Sheets of Saint-Gobain Formula plasters and gypsum minerals are available for all products and may be obtained directly on our website in the [product](#) and [documentation](#) sections. No liability is accepted by Saint-Gobain Formula for injury to any person or loss or damage to property by improper use of the product.

## NOTIFICATION

The plaster to water ratios quoted are those used in Saint-Gobain Formula's standard test methods and are not necessarily those used in practice. The precise consistency to use will need to be adjusted to suit the individual application. Changes to plaster to water ratio will influence product performance, particularly setting time and strength. Unless otherwise stated, Saint-Gobain Formula's standard test methods apply. To obtain a copy of the test method, please contact Saint-Gobain Formula directly. This literature cancels and replaces any previous document. All information given is provided in good faith and may be subject to change. It's advisable to contact Saint-Gobain Formula in case of any doubt arising from the content of such information.

## CONTACT

*For any information, please visit our website  
[www.saintgobainformula.com](http://www.saintgobainformula.com)*



*Sales  
contact*



*Documentation*



*Technical  
information*



*Global  
information*